



RTV6126-D1

***Product Selector Guide
RTV6100 Series
Silicone Dielectric Gels***

Product Description RTV silicone dielectric gels are low viscosity liquid silicones which cure to form very soft, gel-like elastomers. They are specifically designed to preserve dielectric integrity and provide outstanding protection to delicate electronic circuit assemblies operating in harsh environments. These clear, solventless, two component materials are supplied with curing agents in matched kits which are designed for use at a convenient 1:1 ratio by weight.

When cured, silicone gels possess unique physical properties, combining the self-healing characteristics of a liquid with the non-flowing, dimensional stability of an elastomer. The soft nature and cushioning effect of these semi-solid materials provides excellent protection of electronic assemblies from external shock and vibration. These critical properties are not significantly affected by high and low temperature extremes. This ability, combined with their low modulus properties, makes silicone gels one of the most effective means of managing thermal stress related failures in hybrids and other circuitry utilizing surface mounted devices (SMD's) and other stress sensitive devices.

RTV6126-D1 - An extremely fast curing silicone gel which offers cure times of less than one hour at room temperature. Due to its very short pot-life, automated meter-mix dispensing equipment is required.

RTV6136-D1 - A "high strength", tough silicone gel which offers much better tear resistance properties than conventional gels. It also offers cure times of less than four hours at room temperature. Due to its relatively short pot-life, automated meter-mix dispensing equipment is recommended.

RTV6156 - A high performance methyl-phenyl silicone gel specifically formulated to offer extended low temperature performance.

RTV6166 - A general purpose silicone gel offering the excellent performance of a silicone with cost effectiveness.

RTV6186 - A "high strength", tough silicone gel which offers much better tear resistance properties than conventional gels. It also offers extended room temperature pot-life (8+ hours) for effective use on non-automated production lines.

RTV6196 - A very fast curing silicone gel which offers cure times of less than two hours at room temperature. Due to its short pot-life, automated meter-mix dispensing equipment is strongly recommended.

**Key Performance
Properties**

- Extremely soft, low modulus elastomeric properties
- Outstanding stress-relief properties
- Mechanical shock/vibration dampening properties

- Primerless adhesion to many substrates
- Excellent dielectric properties
- Excellent moisture protection properties
- Low toxicity, solventless formulation
- Probe testable/self-healing/repairable
- Low viscosity to ensure complete coverage
- Heat accelerated or room temperature cure
- Extended low/high temperature performance
- Low shrinkage, non-exothermic cure
- Optical clarity allows visual inspections

Typical Product Data

Uncured Properties (as catalyzed 1:1 by weight)	RTV6126-D1	RTV6136-D1	RTV6156	RTV6166	RTV6186	RTV6196
Appearance	clear, colorless	clear, colorless	clear, colorless	clear, colorless	clear, colorless	clear, colorless
Viscosity, cps (25°C/77°F)	750	750	750	750	750	750
Specific Gravity	0.98	0.98	0.98	0.98	0.98	0.98
Pot Life (25°C/77°F)	5 minutes	30 minutes	1 hour	2 hours	8+ hours	15 minutes
Cured Properties (cured 30 minutes/150°C)						
Physical						
Penetration, mm (25°C/77°F)	6.5	6.0	4.0	6.0	6.0	6.0
Useful Temperature Range, °C	-50 to 204	-50 to 204	-115 to 235	-50 to 204	-50 to 204	-50 to 204
(°F)	(-58 to 400)	(-58 to 400)	(-175 to 500)	(-58 to 400)	(-58 to 400)	(-58 to 400)
Refractive Index	1.41	1.41	1.43	1.41	1.41	1.41
Electrical						
Dielectric Strength, v/mil @75 mils	500	500	500	500	500	500
Dielectric Constant (1000 Hz)	2.8	2.8	2.8	2.8	2.8	2.8
Dissipation Factor (1000 Hz)	0.001	0.001	0.001	0.001	0.001	0.001
Volume Resistivity, Ohm-cm	1 X 10 ¹⁵	1 X 10 ¹⁵	1 X 10 ¹⁵	1 X 10 ¹⁵	1 X 10 ¹⁵	1 X 10 ¹⁵

Specifications Typical product data values should not be used as specifications. Assistance and specifications are available by contacting Momentive Performance Materials at 800/255-8886.

Instructions for Use **INSTRUCTIONS FOR USE**

Compatibility



The RTV6100 series silicone dielectric gels will cure in contact with most clean and dry surfaces. However, certain materials, such as butyl and chlorinated rubber, sulfur-containing materials, amines, and certain metal soap cured RTV silicone rubber compounds can cause cure inhibition. Cure inhibition is characterized by a lack of cure of the silicone gel at the interface between it and the substrate. Compatibility tests should be performed on all materials in contact with the uncured gel, including painted surfaces.

Surface Preparation

The adhesive performance of any polymer system is highly dependent upon proper surface preparation. In order to maximize the adhesion of the RTV6100 series silicone dielectric gels and minimize the potential for cure inhibition, all parts should be as clean and dry as possible prior to the application of the silicone gel. In addition to minimizing the potential for cure inhibition, clean parts also minimize long term reliability problems which can be caused by contaminants trapped under the silicone gel.

Bonding

The RTV6100 series silicone dielectric gels offer excellent, reformable, pressure sensitive adhesion characteristics to a wide variety of substrates without the need of a primer.

For difficult-to-bond-to substrates, or where more aggressive chemical adhesion is desired, the adhesion may be enhanced by using SS4155 silicone primer, available from Momentive Performance Materials. To apply the primer, thoroughly clean the surface and let dry. Then apply a uniform film (0.01-0.02 mm / 0.5-1.0 mil) of SS4155 silicone primer and allow the primer to air-dry for one hour or more. When dry, SS4155 silicone primer exhibits a white haze which will show through the silicone gel. If the appearance of the surface to be bonded must be unchanged, SS4120 silicone primer, also available from Momentive Performance Materials may be used. For more details on priming and adhesion, please refer to Momentive Performance Materials product data sheet on silicone primers.

Mixing

The RTV6100 series silicone dielectric gels are kit-matched products. As such, work time (pot-life), cure time, and final cured properties can only be assured if the batch numbers on the A component and B component are identical and the material is mixed at a ratio of 1:1 (by weight).

To hand mix, select a clean mixing container 4-5 times larger than the volume of RTV silicone gel to be used. Weigh out equal amounts of the A & B components. With clean tools, thoroughly mix the A & B components together, scraping the sides and bottom of the container carefully to produce a homogeneous mixture. Care should be taken to minimize the amount of air entrapment. Vacuum deaeration (25 mm mercury) can be used to remove entrapped air from the uncured mixture.

Due to their extremely short work life, mixing of RTV6126-D1, RTV6136-D1, and RTV6196 for use in continuous or high volume production environments should be done via automated meter/static-mix dispensing equipment. The use of dynamic mixing equipment or hand-mixing is not recommended.

The final cured properties of the RTV6100 series silicone dielectric gels can be altered by changing the mix ratio of the two components. Increasing the ratio of Part A to Part B will yield a softer gel (i.e. higher penetration value). Likewise, decreasing the ratio of Part A to Part B will result in a gel with a lower penetration value. Deviations greater than 10% from the standard 1:1 mix ratio are not recommended. Changes to the mix ratio will affect the pot-life of the catalyzed mixture.



Pot-Life and Cure Time Comparisons

Product	Pot-life	Cure Time (1:1) Mix Ratio			
		25 °C (77 °F)	25 °C (77 °F)	65 °C (149 °F)	100 °C (212 °F)
RTV6126-D1	5 mins	< 1 hr	20 mins	5 mins	2 mins
RTV6196	15 mins	< 2 hrs	1 hr	10 mins	5 mins
RTV6136-D1	30 mins	< 4 hrs	2 hrs	20 mins	10 mins
RTV6156	1 hr	< 18 hrs	4 hrs	1 hr	15 mins
RTV6166	2 hrs	< 24 hrs	4 hrs	1 hr	15 mins
RTV6186	8+ hrs	N/A*	4 hrs	1 hr	15 mins

*Requires minimum cure temperature of 60 °C

When used, ovens must be well ventilated.

CURE TIMES ARE ONLY APPROXIMATE. THE ACTUAL TIME IS AFFECTED BY THE MASS OF THE GEL AND THE TIME REQUIRED TO REACH THE DESIRED TEMPERATURE.

Equipment

Automatic equipment designed to meter, mix, and dispense two-component RTV silicone gels will add convenience and reliability to continuous or large volume operations. Specific details on dispensing systems and manufacturers are available in a separate RTV Silicone Rubber Equipment Guide (Momentive Performance Materials Publication # CDS1758).

Handling and Safety Material Safety Data Sheets are available upon request from Momentive Performance Materials. Similar information for solvents and other chemicals used with Momentive Performance Materials Products should be obtained from your suppliers. When solvents are used, proper safety precautions must be observed.

CAUTION

The curing agent ("B" component) of the RTV6100 series dielectric silicone gels can generate flammable hydrogen gas upon contact with acidic, basic, or oxidizing materials. Such contact should be avoided.

Storage and Warranty Period The warranty period for the RTV6100 series dielectric silicone gels is 12 months from date of shipment from Momentive Performance Materials if stored in the original unopened containers at temperatures of 25 °C (77 °F) or below.

Availability The RTV6100 series dielectric silicone gels may be ordered from Momentive Performance Materials, Waterford, NY 12188, the Momentive Performance Materials sales office nearest you or an authorized Momentive Performance Materials product distributor.

Government Requirement Prior to considering use of a Momentive Performance Materials product in fulfilling any Government requirement, please contact the Government and Trade Compliance office at 413-448-4624.

CDS4776

reinhardoil.dk

Telefon + 45 70267007

Telefax + 45 70267047

www.reinhardoil.dk

mail@reinhardoil.dk

LEGAL DISCLAIMER

THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS, THEIR SUBSIDIARIES OR AFFILIATES (THE "SUPPLIER"), ARE SOLD SUBJECT TO THE SUPPLIER'S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN APPLICABLE SALES AGREEMENTS, PRINTED ON THE BACK OF ACKNOWLEDGMENTS AND INVOICES, OR AVAILABLE UPON REQUEST. ALTHOUGH THE INFORMATION, RECOMMENDATIONS OR ADVICE CONTAINED HEREIN



IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (I) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (II) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING SUPPLIER'S MATERIALS, PRODUCTS, SERVICES, RECOMMENDATIONS OR ADVICE. NOTHING IN THIS OR ANY OTHER DOCUMENT SHALL ALTER, VARY, SUPERSEDE OR OPERATE AS A WAIVER OF ANY OF THE SUPPLIER'S STANDARD CONDITIONS OF SALE.

Each user bears the full responsibility for making its own determination as to the suitability of Supplier's materials, products, services, recommendations or advice for its own particular purpose. Each user must identify and perform tests and analyses sufficient to assure it that its finished parts will be safe and suitable for use under end-use conditions. Because actual use of products by the user is beyond the control of Supplier, such use is within the exclusive responsibility of the user, and Supplier cannot be held responsible for any loss incurred through incorrect or faulty use of the products. Further, no statement contained herein concerning a possible or suggested use of any material, product, service or design is intended or should be construed to grant any license under any patent or other intellectual property right of Supplier or any of its subsidiaries or affiliated companies, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

reinhardoil.dk

Telefon + 45 70267007

Telefax + 45 70267047

www.reinhardoil.dk

mail@reinhardoil.dk

