

IS 802 , IS 803 , IS 808

One component RTV Adhesive/Sealants

Product Description IS802, IS803 and IS808 one-component, ready-to-use silicone adhesive sealants are a paste-like consistency and cure to silicone rubber on exposure to atmospheric moisture at room temperature. Because these paste-consistency products will flow only with external pressure, they may be applied to horizontal, vertical and overhead surfaces in thicknesses up to 10 mm. They have sufficient uncured body to adhere to small objects while cure is taking place. IS802, IS803 and IS808 adhesive sealants utilize a moisture vapour cure system and release acetic acid vapours from the sealant surface as a by-product of cure.

The following products are identical materials and differ only in colour:
IS802 - White
IS803 - Black
IS808 - Translucent

Key Performance Properties

- One-component product
- Thixotropic (paste-like) consistency
- Capability to cure at room temperature and ambient humidity conditions
- Excellent dielectric properties
- Excellent weatherability, ozone and chemical resistance
- Self-adhesion properties
- Low temperature flexibility
- High temperature performance

Applications The paste-like consistency of IS802, IS803 and IS808 adhesive sealants makes these products ideally suited for application to vertical and overhead surfaces where use of pourable self-leveling sealants would not be practical. These paste-consistency silicone sealant may be used in thicknesses up to 10 mm for bonding and sealing, joining metals and plastics.

These sealants are not for use in delicate electrical and electronic applications in which corrosion of copper, brass or other sensitive metals is undesirable.

For applications requiring sealant thicknesses greater than 10 mm, Momentive performance materials two component silicone rubber compounds are recommended.

Typical Product Data **Typical Uncured Properties:**

Consistency	Soft, spreadable paste
Specific gravity (g/cm ³)	1.04
Application rate (g/min.)	410
Tack Free time (minutes)	25

Typical Cured Properties:

Hardness (shore A)	23
Tensile strength (MPa)	2.0
Elongation (%)	450
Shear Adhesion @ 100 % cohesive failure (MPa)	1.0

Electrical Properties:

Dielectric Strength (kV/mm)	20
Dielectric constant @ 50 Hz	2.9
Dissipation factor @ 50 Hz	0.0026
Volume resistivity (ohm· cm)	2.5x10 ¹⁴

1) obtained on 2 mm thick ASTM slabs cured for 3 days at 23°C and 50% RH

2) obtained on 1 mm thick slabs cured for 3 days at 23° C/50% RH

Specifications Typical product data values should not be used as specifications. Assistance and specifications are available by contacting Momentive performance materials Technical Service RTV 1 and RTV 2.

FDA STATUS

IS802, IS803 and IS808 can be used in food contact applications when FDA regulations apply.

USDA STATUS

IS802, IS803 and IS808 sealants may be used on equipment which may contact edible products in official establishments operating under the Federal Meat and Poultry Products Inspection Program.

NSF INTERNATIONAL STATUS

NSF International lists IS802, IS803 and IS808 sealants under NSF International Standard No. 51 (Plastic Materials and Components for Use in Food Equipment), as satisfactory for use on food contact surfaces.

UL STATUS

IS802, IS803 and IS808 silicone rubber adhesive sealants are recognized by Underwriters Laboratories, Inc. under their Component Recognition Program (UL File No E36952). Refer to GE publication no. (4320) "Underwriters' Laboratories Recognition for Silicone Rubber Adhesive Sealants" for additional information.

Instructions for Use

Surface preparation:

IS802, IS803 and IS808 adhesive sealants will bond to many clean surfaces. These surfaces typically include many metals, glass, ceramic, silicone rubber and some rigid plastics. These silicone adhesive sealants will also produce fair bonds to flexible plastics not containing fugitive plasticizers (which migrate to the surface impairing adhesion). An evaluation should be made to determine bond strength for each specific applications. For difficult to bond substrates use of a primer is suggested. Momentive performance materials primers such as SS4004P, SS4044P, SS4155 and SS4179 are recommended for use with these adhesive sealants. If the evaluation of IS802, IS803 or IS808 sealants indicates that greater adhesion levels are required, Momentive performance materials Silicone products such as RTV102, RTV103 or RTV108 should be considered.

For optimum adhesion, surfaces should be thoroughly cleaned with a suitable solvent to remove dirt, oil and grease. The surface should be dry before applying the silicone sealant.

Application and cure time cycle:

Momentive performance materials paste consistency silicone adhesive sealants may be applied directly to the clean (or primed) substrate. Where broad surfaces are to be mated, the adhesive sealant should be applied in a thin, less than 10 mm diameter, bead or ribbon around the edge of the surface to be bonded.

The cure process begins with the formation of a skin on the exposed surface of the adhesive sealant and progresses inward through the material. At 25 C and 50 % relative humidity, these products will form a surface skin which is typically tack free to touch in 20 to 30 minutes. Once the tack free skin has begun to form, further tooling of the silicone adhesive is not advisable.

High temperatures and high humidity will accelerate the cure process low temperatures and low humidity will slow the cure rate.

As the silicone adhesive sealant cures, acetic acid vapours are released from the adhesive sealant surface. The odour of acetic acid will completely disappear when the cure is completed.

In addition to the effects of temperature and relative humidity, development of maximum physical properties will depend on joint configuration, degree of confinement, sealant thickness and substrate porosity.

A 3 mm section of silicone adhesive sealant will cure through in approximately 24 hours at 25 C and 50 % relative humidity. Since cure time increases with thickness, use of IS802, IS803 and IS808 silicone adhesive sealants should be limited to thicknesses of 10 mm or less. Normally, sufficient strength will develop in 12 to 24 hours to permit handling of parts. Minimum stress should be applied to the silicone sealant until full physical properties are developed.

Dispensing:

Collapsible tubes may be squeezed by hand or with the aid of mechanical wringers. Air operated dispensing guns may also be used with tubes and offer the advantages of improved control and faster application for production line use. Dispensing from caulking cartridges using simple mechanical caulking guns or air operated guns. Both tubes and cartridges are easy to use, can be put into production quickly and require minimal capital investment.

Bulk containers require a larger investment in dispensing equipment, but offer economical packaging for volume production. Bulk dispensing systems are air-operated extrusion pumps coupled to hand or automated dispensing units. Pumps which are specifically designed for one component condensation cure materials have Teflon seals, packings and Teflon lined hoses to prevent moisture penetration and pump cure problems. Specific details on dispensing systems and manufacturers are available upon request from Momentive performance materials.

Clean up and Removal:

Before cure, solvent systems such as naphtha or methyl ethyl ketone (MEK) are effective.

After cure, selected chemical strippers which will remove the silicone rubber are available from other manufacturers. Specific product information may be obtained on request.

Handling and Safety

Material Safety Data Sheets are available from Momentive performance materials. Similar information for solvents and other chemicals used with our products may be obtained from your supplier.

**Storage and Warranty
Period**

The shelf life is indicated by the "use before date" on the associated documents with a minimum of 4 months when stored in the original unopened containers at a temperature of max 27 C.

Availability

IS802, IS803 and IS808 are supplied ready to use in collapsible squeeze tubes, cartridges and in bulk containers.



PRINCIPAL LOCATIONS – Regional Information

North America	World Headquarters 187 Danbury Road Wilton, CT 06897, USA	T 800.295.2392	F 607.754.7517
Latin America	Rodovia Eng. Constâncio Cintra, Km 78,5 Itatiba, SP – 13255-700, Brazil	T +55.11.4534.9650	F +55.11.4534.9660
Europe, Middle East, Africa and India	D-51368 Leverkusen Germany	T 00.800.4321.1000 T +31.164.293.276	F +31.164.241.750
Pacific	Akasaka Park Building - 5-2-20 Akasaka Minato-ku, Tokyo 107-6112 Japan	T +81.3.5544.3100	F +81.3.5544.3101

CUSTOMER SERVICE CENTERS

North America	Charleston, WV 25314, USA E cs-na.silicones@momentive.com		
	• Specialty Fluids	T 800.523.5862	F 304.746.1654
	• UA, Silanes, Resins, and Specialties	T 800.334.4674	F 304.746.1623
	• RTV Products-Elastomers	T 800.332.3390	F 304.746.1623
	• Sealants and Adhesives & Construction	T 877.943.7325	F 304.746.1654
Latin America	E cs-la.silicones@momentive.com		
	• Argentina & Chile	T +54.11.4862.9544	F +54.11.4862.9544
	• Brazil	T +55.11.4534.9650	F +55.11.4534.9660
	• Mexico & Central America	T +52.55.5899.5135	F +52.55.5899.5138
	• Venezuela, Ecuador, Peru, Colombia, & Caribbean	T +58.212.285.2149	F +58.212.285.2149
Europe, Middle East, Africa and India	E cs-eur.silicones@momentive.com	T 00.800.4321.1000 T +31.164.293.276	F +31.164.241750
	E cs-ap.silicones@momentive.com		
Pacific	• Japan	T +81.276.20.6182	
	• China	T +86.21.5050.4666 (ext. 1523)	
	• Korea	T +82.2.6201.4600	
	• Singapore	T +65.6220.7022	
Worldwide Hotline	Worldwide Web www.momentive.com	T 800.295.2392 T +607.786.8131	F +607.786.8309

DISCLAIMER: THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC., MOMENTIVE PERFORMANCE MATERIALS USA INC., MOMENTIVE PERFORMANCE MATERIALS ASIA PACIFIC PTE. LTD., MOMENTIVE PERFORMANCE MATERIALS WORLDWIDE INC., MOMENTIVE PERFORMANCE MATERIALS GmbH & Co. KG, MOMENTIVE PERFORMANCE MATERIALS SUISSE Sarl, THEIR SUBSIDIARIES AND AFFILIATES DOING BUSINESS IN LOCAL JURISDICTIONS (collectively "SUPPLIERS"), ARE SOLD BY THE RESPECTIVE LEGAL ENTITY OF THE SUPPLIER SUBJECT TO SUPPLIERS' STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIERS MAKE NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING SUPPLIERS' PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. AFOREMENTIONED EXCLUSIONS OR LIMITATION OF LIABILITY ARE NOT APPLICABLE TO THE EXTENT THAT THE END-USE CONDITIONS AND/OR INCORPORATION CONDITIONS CORRESPOND TO THE RECOMMENDED CONDITIONS OF USE AND/OR OF INCORPORATION AS DESCRIBED BY SUPPLIER IN ITS PRODUCT DATA SHEET AND/OR PRODUCT SPECIFICATIONS.

EXCEPT AS PROVIDED IN SUPPLIERS' STANDARD CONDITIONS OF SALE, SUPPLIERS AND THEIR REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN.

Each user bears full responsibility for making its own determination as to the suitability of Suppliers' materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Suppliers' products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Suppliers' Standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Suppliers. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Suppliers or any of its subsidiaries or affiliates covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.