




2016-10-14		ProLube Medical White Oils 7 to 100 cSt./40°C												SHARE	
Ref LabRap 20140724		10-FG(10-LV2)		15-FG		22 FG		32-FG		46-FG		68-FG			
ISO NR		ISO 7 / 10		ISO 15		ISO 22		ISO 32		ISO 46		ISO 68			
Type SUS /100°F		60		80		100		150		250		350			
	Unit	Spec	Typ	Spec	Typ	Spec	Typ	Spec	Typ	Spec	Typ	Spec	Typ		
Apearance		Br & Cl	Br & Cl	Br & Cl	Br & Cl	Br & Cl	Br & Cl	Br&Cl	Br & Cl	Br. &Cl	Br. & Cl.	Br&Cl	Br&Cl		
Density 15°C		0.815-0.825	0,819	0.821 - 0.836	0,8353	0,835.0,845	0,8393		0,8424		0,8626	0,853-	0,8576		
Density 25°C		0.81-0.82	0,814	0.815-0.830	0,825	0,825-0,830	0,83		0,833		0,86	0,848-0,868	0,851		
Viscosity 0°C	cSt		34		91		132		371				880		
Viscosity Dy.20°C	mPas		14,5		28,75		44		61,89	115-135	120,2		171,2		
Viscosity Ki 40°C	cSt	7.0-11.0	7,6	14.0-17.0	15,72	min. 20,5	21		29,86	48-56	49,4		69,08		
Viscosity Ki 100°C	cSt.		2,27		3,5		4,48		5,65		7,32		9,14		
Viscosity Index			110		105		128		132		108		107		
Flash point	°C	145	158	160	188	180	220	180	220	200	218	200	252		
Pour point	°C	max -15	-18	max -15	÷21	max ÷12	÷21	max ÷ 12	÷21	max ÷9	÷21	max ÷ 9	÷ 21		
Anilin point	°C		106		110		114		106				120		
Colour Saybolt		30	30	30	30	30	30	30	30	30	30	30	30		
Readily c.S.		Passes	Passes	Passes	Passes	Passes	Passes	Passes	Passes	Passes	passes	Passes	Passes		
Acidity/alkanity		Passes	Passes	Passes	Passes	Passes	Passes	Passes	Passes	Passes	passes	Passes	Passes		
Sulphur Compounds		Passes	Passes	Passes	Passes	Passes	Passes	Passes	Passes	Passes	passes	Passes	Passes		
solid paraffin		Passes	Passes	Passes	Passes	Passes	Passes	Passes	Passes	Passes	Passes	Passes	Passes		
polynuclear compounds		Passes	Passes	Passes	Passes	Passes	Passes	Passes	Passes	Passes	Passes	Passes	Passes		
Refraktive Index			1,452		1,462		1,4616		1,4581		1,471		1,4767		
Carbon Type P/N/A%	%	P-65,N-35	A-0	P-62,N-38	A-0	P67 N 33	A 0	P-71 N- 29 A-0		P-63 N-37	A-0	P-63, N-37	A-0		
NSF H1 status		Conforms	Conforms	Conforms	Conforms	Conforms	Conforms	Conforms	Conforms	Conforms	Conforms	Conforms	Conforms		
Kosher Status		Conforms	Conforms	Conforms	Conforms	Conforms	conforms	Conforms	Conforms	Conforms	Conforms	Conforms	Conforms		
EP		Conforms	Conforms	Conforms	Conforms	conforms	Conforms	Conforms	Conforms	Conforms	Conforms	Conforms	Conforms		
USP		Conforms	Conforms	Conforms	Conforms	conforms	Conforms	Conforms	Conforms	Conforms	Conforms	Conforms	Conforms		
DAB		Conforms	Conforms	Conforms	Conforms	Conforms	Conforms	Conforms	Conforms	Conforms	Conforms	Conforms	Conforms		
cSt.more correctly replaced by mm2/sec		G-II		G-II		G-II		G-II		G-II		G-II			
Batch Number															
NSF H1 HX-1 3H status		yes		137541		137542		137543		fullfill InS & NSF		137546			
Sales & Technical Services:															
ReinhardOil. DK ApS (Ltd.)		Pro Lube													
info@reinhardoil.dk															
fax+45 70 26 70 47															
Supplied ind drums from Stock in Kolding and Copenhagen Denmark															
HS Code for ProLube Med. White oils is: 27.10.19.85															
CAS 8042-47-5															

12-FG		100-FG	
ISO 10 / 15		ISO 100	
70		500	
Spec	Typ	Spec	Typ
Br & Cl	Br & Cl	Br & Cl	Br & Cl
0.819-0.833	0,825		0,865
0.814-0.828	0,82		0,86
	69		1150
	19,52		275
11.0-14.0	12,48	85-100	94
	3,16		10,7
	117		110
150	188	220	230
÷15	<÷21	÷ 6	÷ 9
	103		
30	30	30	30
Passes	Passes	Passes	Passes
Passes	Passes	Passes	Passes
Passes	Passes	Passes	Passes
Passes	Passes	Passes	Passes
Passes	Passes	Passes	Passes
	1,459		1,4671
P-65,N-35	A-0	P-68,N-32	A-0
Conforms	Conforms	Conforms	Conforms
Conforms	Conforms	Conforms	Conforms
Conforms	Conforms	Conforms	Conforms
Conforms	Conforms	Conforms	Conforms
Conforms	Conforms	Conforms	Conforms
	G-II		G-II
	yes	137547	
			
		Tel:+4570267007	