



ReinhardOil.dk  
 Helleruplund Alle 8  
 DK-2900 Hellerup  
 Tel: +45 70 26 70 07  
 CVR 32659470  
 www.reinhardoil.dk

## RTV162

*RTV160, RTV162 and RTV167*  
*Electronic Grade Silicone Adhesive Sealants*

**Product Description** RTV160, RTV162 and RTV167 adhesive sealants from Momentive Performance Materials are one-component, ready-to-use electronic grade silicone sealants. They cure to a tough, resilient silicone rubber on exposure to atmospheric moisture at room temperature. These electronic-grade silicone adhesive sealants differ somewhat in physical properties including consistency.

RTV160 - white flowable paste  
 RTV162 - white paste  
 RTV167 - gray, high strength paste

- Key Performance Properties**
- Non-corrosive to electronic metals, including copper and brass
  - Low odor cure, releasing an alcohol vapor from the sealant surface during cure
  - UL Recognition. RTV160, RTV162 and 167 are recognized by Underwriters Laboratories, Inc. under their Component Recognition Program (UL File No. E-36952). Refer to Momentive Performance Materials Publication (4320) for additional information.
  - Retains elastomeric properties for long periods at temperatures from -60C (-75F) to 205C (400F) and for short periods up to 260C (500F).
  - One component
  - Cure at room temperature
  - Excellent electrical insulation properties
  - Excellent resistance to moisture, dust, dirt, UV, ozone and chemicals

**Typical Product Data**

Typical Uncured Properties	RTV160	RTV162	RTV167
Color	White	White	Gray
Consistency	flowable liquid	spreadable paste	spreadable paste
Viscosity, poise	380	-	-
Specific Gravity	1.04	1.09	1.12
Application Rate, gm/min.	-	350	180
Tack-Free Time, hours	4	4	4
<b>Cured Properties<sup>(1)</sup></b>			
<b>Mechanical</b>			
Hardness, Shore A	25	35	37
Tensile Strength, kg/cm <sup>2</sup> (lb/in <sup>2</sup> )	19 (275)	38.2 (550)	56 (800)
Elongation, %	230	400	600
Peel Strength, kg/cm (lb/in) <sup>(2)</sup>	2 (10)	7.2 (40)	10 (80)
<b>Electrical <sup>(3)</sup></b>			
Dielectric Strength, kv/mm (v/mil)	20 (500)	18 (450)	20 (500)
Dielectric Constant @ 60 Hz	2.8	2.8	2.8
Dissipation Factor @ 60 Hz	.001	.001	.0026
Volume Resistivity, ohm-cm	4x10 <sup>14</sup>	3x10 <sup>15</sup>	3x10 <sup>15</sup>
<b>Thermal<sup>(3)</sup></b>			
Brittle Point, °C (°F)	-60 (-75)	-60 (-75)	-60 (-75)
Maximum continuous operating temperature, °C (°F)	204 (400)	204 (400)	204 (400)
Maximum intermittent operating temperature, °C (°F)	260 (500)	260 (500)	260 (500)

Additional Information <sup>(3)</sup>			
Thermal Conductivity, cal/sec/cm <sup>2</sup> , °C/cm	.0005	.0005	.0005
(Btu/hr/ft <sup>2</sup> , °F/f)	(.12)	(.12)	(.12)
Coefficient of Expansion	27x10 <sup>-5</sup>	27x10 <sup>-5</sup>	27x10 <sup>-5</sup>
cm/cm, °C (in/in, °F)	(15x10 <sup>-5</sup> )	(15x10 <sup>-5</sup> )	(15x10 <sup>-5</sup> )

- (1) Cure time 7 days at 25C (77F), 50% relative humidity.
- (2) 1 in. x 8 in. stainless steel screen at 180° pull angle.
- (3) Information is provided for customer convenience only. Properties are not tested on a routine basis.

**Specifications** Typical product data values should not be used as specifications. Assistance and specifications are available by contacting Momentive Performance Materials at 800/255-8886

**MILITARY SPECIFICATIONS**

RTV162 and RTV167 sealants meet the physical requirements of MIL-A-46146. Testing is performed in accordance with current Momentive Performance Materials quality test methods, laboratory conditions, and procedures, frequency and sampling, which are not necessarily identical with the methods, conditions, procedures, frequency and sampling stated or referenced in MIL-A-46146. Any certification will be limited to listed properties and will not imply or state conformity to any other aspect of MIL-A-46146, including but not limited to marking, packaging, bar coding, testing, or sampling. Contact Momentive Performance Materials for a comparison review.

**Instructions for Use**

**Applications**

RTV160, RTV162 and RTV167 are recommended for use in aerospace, automotive, appliance and other industries which incorporate electronic components into a finished product. Electronic and integrated circuits, semiconductors and copper connections are typical applications.

RTV160 adhesive sealant is recommended for insulating, encapsulating and coating in thin sections [less than 6mm (1/4)], where flow into small crevices or hard-to-reach places is desired.

RTV162 adhesive sealant is recommended for sealing and bonding of electronic components onto printed circuit boards and protecting copper connections on electronic parts assemblies.

RTV167 adhesive sealant is recommended for sealing and bonding where high strength would be required.

**Surface Preparation**

RTV160, RTV162 and RTV167 adhesive sealants will bond to many clean surfaces without the aid of primers. These surfaces normally include many metals, glass, ceramic, silicone rubber and some rigid plastics. These adhesive sealants will also bond to some organic rubbers and flexible plastics not containing fugitive plasticizers (those that migrate to the surface impairing adhesion). An evaluation should be made to determine bond strength for each specific application.

For difficult-to-bond substrates, use of a primer is suggested. SS4004, SS4044 and SS4179 primers are recommended for use with RTV160, RTV162 and RTV167 sealants. Complete information and usage instructions for these primer products are contained in a separate product data sheet, (CDS#1532).

Where adhesion is required, surfaces should be thoroughly cleaned with a suitable solvent to remove dirt, oil and grease. The surface should be dry before applying the adhesive sealant.

When solvents are used, proper safety precautions must be observed.

**Cure Time Cycle**

RTV160, RTV162 and RTV167 adhesive sealants may be applied directly to a clean or primed substrate. The adhesive sealant begins to cure on exposure to moisture in the air at room temperature. Where broad surfaces are to be bonded the sealant should be applied in a thin, less than 6mm (¼ in.) diameter bead or ribbon around the edge of one of the surfaces.

The cure process begins with the formation of a skin on the exposed surface of the sealant and progresses inward through the material. At 25C (77F) and 50% relative humidity, these products will form a surface skin which is tack-free to the touch in about 4 hours. Once the tack-free skin has begun to form, further tooling of the adhesive sealant is not advisable.

High temperatures and high humidity will accelerate the cure process low temperatures and low humidity will slow the cure rate.

As the adhesive sealant cures, alcohol vapors are released from the sealant surface. This by-product of cure has a slight, but non-objectionable odor which will completely disappear after curing is completed.

A 3mm (1/8 in.) section of adhesive sealant will cure through in approximately 48 hours at 25C (77F) and 50% relative humidity. Since cure time increases with thickness, use of RTV160, RTV162 and RTV167 sealants should be limited to section thicknesses of 6mm (¼ in.) or less.

**PACKAGING AND DISPENSING**

RTV160, RTV162, RTV167 adhesive sealants are supplied in caulking cartridges and bulk containers. RTV162 and RTV167 are also available in collapsible squeeze tubes.

Tubes may be squeezed by hand or with the aid of mechanical wringers which allow more complete removal of material from the tube. The sealant may be dispensed from caulking cartridges by using simple mechanical caulking guns or air-operated guns. Air-operated guns will allow greater control and application speed. Both tubes and cartridges are easy to use, can be put into production quickly and require minimum capital investment.

**Note:** Do not exceed 45 psig when used in air-powered caulking guns. Bulk containers offer the most economical packaging for volume production.

Bulk dispensing systems are air-operated extrusion pumps coupled to hand or automated dispensing units. Specific details on dispensing systems and manufacturers are available in a separate Momentive Performance Materials RTV Silicone Sealant Equipment Guide, (CDS1541).

Recommendations for pump selection and assistance in converting lines from other silicone systems to the RTV160, RTV162 and RTV167 alkoxy cure system sealants are available from Momentive Performance Materials.

**CLEAN UP AND REMOVAL**

Before cure, solvent systems such as naphtha or methyl ethyl ketone (MEK) are effective.

**Handling and Safety**

Material Safety Data Sheets are available upon request from Momentive Performance Materials. Similar information for solvents and other chemicals used with our products should be obtained from your suppliers.

**Storage and Warranty Period**

The warranty period is 6 months from date of shipment from Momentive Performance Materials if stored in the original unopened container at or below 50°F.

**Availability**

Products may be ordered from Momentive Performance Materials, Waterford, NY 12188, the Momentive Performance Materials Sales office nearest you, or where appropriate an authorized Momentive Performance Materials silicone product distributor.

**Government Requirement**

Prior to considering use of a Momentive Performance Materials product in fulfilling any Government requirement, please contact the Government and Trade Compliance office at 413-448-4624.

CDS4500

**LEGAL DISCLAIMER**

THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS, THEIR SUBSIDIARIES OR AFFILIATES (THE "SUPPLIER"), ARE SOLD SUBJECT TO THE SUPPLIER'S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN APPLICABLE SALES AGREEMENTS, PRINTED ON THE BACK OF ACKNOWLEDGMENTS AND INVOICES, OR AVAILABLE UPON REQUEST. ALTHOUGH THE INFORMATION, RECOMMENDATIONS OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (I) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (II) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING SUPPLIER'S MATERIALS, PRODUCTS, SERVICES, RECOMMENDATIONS OR ADVICE. NOTHING IN THIS OR ANY OTHER DOCUMENT SHALL ALTER, VARY, SUPERSEDE OR OPERATE AS A WAIVER OF ANY OF THE SUPPLIER'S STANDARD CONDITIONS OF SALE.

Each user bears the full responsibility for making its own determination as to the suitability of Supplier's materials, products, services, recommendations or advice for its own particular purpose. Each user must identify and perform tests and analyses sufficient to assure it that its finished parts will be safe and suitable for use under end-use conditions. Because actual use of products by the user is beyond the control of Supplier, such use is within the exclusive responsibility of the user, and Supplier

cannot be held responsible for any loss incurred through incorrect or faulty use of the products. Further, no statement contained herein concerning a possible or suggested use of any material, product, service or design is intended or should be construed to grant any license under any patent or other intellectual property right of Supplier or any of its subsidiaries or affiliated companies, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.