

FRV1106

Product Description FRV1106 is a one-component, ready-to-use fluorosilicone adhesive sealant that cures to a tough resilient silicone rubber on exposure to atmospheric moisture at room temperature. FRV1106 adhesive sealant is a paste consistency, fluid resistant product designed for use in fuel, solvent and chemical environments.

Key Performance Properties Resists swelling by hydrocarbon solvents, dimethyl silicone fluids and fuels.

- One component product
- Primerless adhesion to many substrates
- Room Temperature Cure
- Non-sag paste consistency
- Retain elastomeric properties at temperatures of -60C to 204C for long periods and to 260C for short periods.
- Ozone resistant, high quality weatherability
- Excellent electrical insulation properties

Applications FRV1106 adhesive sealant is ideally suited for use in applications where resistance to the swelling effects of fuels, oils, solvents and chemicals is needed. Providing a formed-in-place gasket for pipe junctions in chemical plants, sealing seams on liquid holding tanks and bonding sensing devices in a gas tank are typical applications. The paste consistency of these sealants allows them to be applied even on vertical and overhead surfaces in thickness up to 6mm .

Typical Product Data

Uncured Properties	
Colour	Red
Consistency	Paste
Specific Gravity, g/cm ³	1.45
Application Rate, g/min.	88
Tack Free Time, minutes	20
Cure Through Time, hours	24
Cured Properties ⁽¹⁾	
Mechanical:	
Hardness, Shore A	39
Tensile Strength, MPa	3.3
Elongation, %	200
Peel Strength, kN/m	4.6



Fluid Immersion Properties ⁽²⁾

	Volume Swell %	Shore A Hardness pts change	Tensile Strength % change	Elongation % change
FRV1106				
Toluene	16.6	-4	-30	-8
Mineral Spirits	2.2	-4	-27	-4
Methylene Chloride	61.0	-8	-29	12
JP-4	5.4	-2	-28	23
Fuel B	17.9	-2	-30	-32

(1) Cured 7 days at 25C and 50% Relative Humidity

(2) Cured 7 days before immersion. Properties obtained after 7 days immersion at room temperature. Information is provided for customer convenience. These properties are not tested on a routine basis.

(3) These sealants are not for use in delicate electrical and electronic applications in which corrosion of copper, brass and other sensitive metals is undesirable.

Specifications Typical product data values should not be used as specifications. Assistance and specifications are available by contacting Momentive performance materials Technical Service RTV1 and RTV2.

Instructions for Use Surface Preparation

FRV1106 adhesive sealant will bond to many surfaces without the aid of a primer. Surfaces should be thoroughly cleaned with a suitable solvent to remove dirt, oil, grease and other contaminants. If scale or corrosion is present, the surface should be cleaned with an abrasive wheel or sandpaper followed by a solvent cleaning.

Application and Cure Time Cycle

FRV1106 adhesive sealant may be applied directly to clean or primed substrates. The cure process begins with the formation of a skin on the exposed surface of the sealant and progresses inward through the material. At 25C and 50% relative humidity, these sealants will form a surface skin that is tack-free to the touch in 20-25 minutes. Once this tack-free skin begins to form, further tooling of the sealant is not recommended.

As the adhesive sealant cures, acetic acid vapors are released. As the curing reaches completion, the noticeable acetic odor will diminish. Because these adhesive sealants cure by reacting with atmospheric moisture higher temperature and humidity will accelerate the cure process while lower temperature and humidity will retard the process. Exact cure time will depend on temperature, humidity, sample thickness and sealant configuration.



PHYSICAL PROPERTY DEVELOPMENT

In addition to the effects of temperature and relative humidity, development of maximum bond strength will depend on joint configuration, degree of confinement, sealant thickness and substrate porosity. Normally, sufficient bond strength for the FRV1106 will develop in 18-24 hours to permit handling of parts. Stress should not be applied to the bonded joint until full adhesive strength has developed. Eventually the adhesive strength of the bond will exceed the cohesive strength of the silicone adhesive sealant itself. Always allow maximum cure time available for best results.

PACKAGING AND DISPENSING

FRV1106 adhesive sealant is supplied ready to use in 150 ml SEMCO® cartridges.

The SEMCO cartridge is designed for use with a hand or air operated sealant gun manufactured by the Semco Company.

CLEAN UP AND REMOVAL

Before curing, solvent systems such as methyl ethyl ketone (MEK) and acetone are most effective. After cure, selected chemical strippers which will remove the silicone rubber are available from other manufacturers. Specific product information may be obtained on request.

Handling and Safety Material Safety Data Sheets are available upon request from Momentive performance materials. Similar information for solvents and other chemicals used with the Momentive performance materials products should be obtained from your supplier. When solvents are used, proper safety precautions must be observed.

Storage and Warranty Period The warranted shelf life will be indicated by the 'use before date' on the associated documents with a minimum of 4 months when stored in the original unopened containers below 25° C.

Availability FRV1106 is available in 150 ml SEMCO® cartridges.





PRINCIPAL LOCATIONS – Regional Information

North America	World Headquarters 187 Danbury Road Wilton, CT 06897, USA	T 800.295.2392	F 607.754.7517
Latin America	Rodovia Eng. Constâncio Cintra, Km 78,5 Itatiba, SP – 13255-700, Brazil	T +55.11.4534.9650	F +55.11.4534.9660
Europe, Middle East, Africa and India	D-51368 Leverkusen Germany	T 00.800.4321.1000 T +31.164.293.276	F +31.164.241.750
Pacific	Akasaka Park Building - 5-2-20 Akasaka Minato-ku, Tokyo 107-6112 Japan	T +81.3.5544.3100	F +81.3.5544.3101

CUSTOMER SERVICE CENTERS

North America	Charleston, WV 25314, USA E cs-na.silicones@momentive.com		
	<ul style="list-style-type: none"> Specialty Fluids UA, Silanes, Resins, and Specialties RTV Products-Elastomers Sealants and Adhesives & Construction 	T 800.523.5862 T 800.334.4674 T 800.332.3390 T 877.943.7325	F 304.746.1654 F 304.746.1623 F 304.746.1623 F 304.746.1654
Latin America	E cs-la.silicones@momentive.com		
	<ul style="list-style-type: none"> Argentina & Chile Brazil Mexico & Central America Venezuela, Ecuador, Peru, Colombia, & Caribbean 	T +54.11.4862.9544 T +55.11.4534.9650 T +52.55.5899.5135 T +58.212.285.2149	F +54.11.4862.9544 F +55.11.4534.9660 F +52.55.5899.5138 F +58.212.285.2149
Europe, Middle East, Africa and India	E cs-eur.silicones@momentive.com	T 00.800.4321.1000 T +31.164.293.276	F +31.164.241750
Pacific	E cs-ap.silicones@momentive.com		
	<ul style="list-style-type: none"> Japan China Korea Singapore 	T +81.276.20.6182 T +86.21.5050.4666 (ext. 1523) T +82.2.6201.4600 T +65.6220.7022	
Worldwide Hotline	Worldwide Web www.momentive.com	T 800.295.2392 T +607.786.8131	F +607.786.8309

DISCLAIMER: THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC., MOMENTIVE PERFORMANCE MATERIALS USA INC., MOMENTIVE PERFORMANCE MATERIALS ASIA PACIFIC PTE. LTD., MOMENTIVE PERFORMANCE MATERIALS WORLDWIDE INC., MOMENTIVE PERFORMANCE MATERIALS GmbH & Co. KG, MOMENTIVE PERFORMANCE MATERIALS SUISSE Sarl, THEIR SUBSIDIARIES AND AFFILIATES DOING BUSINESS IN LOCAL JURISDICTIONS (collectively "SUPPLIERS"), ARE SOLD BY THE RESPECTIVE LEGAL ENTITY OF THE SUPPLIER SUBJECT TO SUPPLIERS' STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIERS MAKE NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING SUPPLIERS' PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. AFOREMENTIONED EXCLUSIONS OR LIMITATION OF LIABILITY ARE NOT APPLICABLE TO THE EXTENT THAT THE END-USE CONDITIONS AND/OR INCORPORATION CONDITIONS CORRESPOND TO THE RECOMMENDED CONDITIONS OF USE AND/OR OF INCORPORATION AS DESCRIBED BY SUPPLIER IN ITS PRODUCT DATA SHEET AND/OR PRODUCT SPECIFICATIONS.

EXCEPT AS PROVIDED IN SUPPLIERS' STANDARD CONDITIONS OF SALE, SUPPLIERS AND THEIR REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN.

Each user bears full responsibility for making its own determination as to the suitability of Suppliers' materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Suppliers' products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Suppliers' Standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Suppliers. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Suppliers or any of its subsidiaries or affiliates covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.