



Teknisk Data

## Grafit pulver 75 MY

Oprindelsesland:

Norge

Specifikation:

Carbon	85-90 %
Aske	10-15 %
Vand	maks. 0,5%
Svovl	maks. 0,4%
Ph	5-7,5



Partikel distribution

+250 um	< 1 %
+125 um	< 3%
+ 75 um	< 15%
-75 um	> 85 %

Typisk Helos distribution:

D <sub>10</sub>	12 - 17 um
D <sub>50</sub>	40 – 55 um
D <sub>90</sub>	90 – 125 um

2019-12-01SQ

**reinhardoil.dk**



Telefon + 45 70267007  
Telefax + 45 70267047  
[www.reinhardoil.dk](http://www.reinhardoil.dk)  
[mail@reinhardoil.dk](mailto:mail@reinhardoil.dk)

[www.ReinhardOil.dk](http://www.ReinhardOil.dk) - T: 70267007