

2022-02-14 K		ProLube Medical White Oils 7 to 100 cSt./40°C								NSF & InS: H1 - 3H & HX-1				SHARE					
Ref LabRap Jan 22 V2		10-FG(10-LV2)		15-FG		22 FG		32-FG		46-FG		68-FG		12-FG		100-FG			
ISO NR		ISO 7 / 10		ISO 15		ISO 22		ISO 32		ISO 46		ISO 68		ISO 10 / 15		ISO 100			
Type SUS /100°F		60		80		100		150		250		350		70		500			
Unit		Spec		Typ		Spec		Typ		Spec		Typ		Spec		Typ			
Appearance		Br & Cl		Br & Cl		Br & Cl		Br & Cl		Br & Cl		Br & Cl		Br & Cl		Br & Cl			
Density 15°C		0.815-0.825		0,825		0.821 - 0,834		0,835.0,845 0,839		0,8424		0,8626 0,853-		0,8576 0.819-		0,825 0,865			
Density 25°C		0.81-0.82		0,814		0.815-0.830		0,825 0,83		0,833		0,86 0,848-0,866		0,851 0.814-		0,82 0,86			
Viscosity 0°C		cSt		34		91		132		371		880		69		1150			
Viscosity Dy.20°C		mPas		14,5		29,42		44		61,89		115-135 120,2		176,12		275			
Viscosity Ki 40°C		cSt		7.0-11.0		8,5 14.0-17.0		15,51 min. 20,5		21,89		29,86 48-56		51 69,08		11.0-14.0 12,48 85-100		94	
Viscosity Ki 100°C		cSt.		2,42		3,66		4,52		5,65		7,32		9,14		3,16		10,7	
Viscosity Index				105		123		123		132		108		117		117		110	
Flash point		°C		145 152		160 180		180 202		180 220		200 218		200 248		150 188		220 230	
Pour point		°C		max -15 -27		max -15 +21		max +12 +21		max + 12 +21		max +9 +21		max + 9 +15		+15 <+21		+ 6 + 9	
Anilin point		°C		106		115		124		106		127		126		103			
Colour Saybolt		30		30		30		30		30		30		30		30		30	
Readily c.S.		Passes		Passes		Passes		Passes		Passes		Passes		Passes		Passes		Passes	
Acidity/alkanity		Passes		Passes		Passes		Passes		Passes		Passes		Passes		Passes		Passes	
Sulphur Compounds		Passes		Passes		Passes		Passes		Passes		Passes		Passes		Passes		Passes	
solid paraffin		Passes		Passes		Passes		Passes		Passes		Passes		Passes		Passes		Passes	
polynuclear compounds		Passes		Passes		Passes		Passes		Passes		Passes		Passes		Passes		Passes	
Refraktive Index		1,456		1,462		1,457		1,4581		1,471		1,4767		1,459		1,4671			
Carbon Type P/N/A%		P-65,N-35 A-0		P-62,N-38 A-0		P67 N 33 A 0		P-71 N- 29 A-0		P-63 N-37 A-0		P-63, N-37 A-0		P-65,N-35 A-0		P-68,N-32 A-0			
NSF H1 status		Conforms		Conforms		Conforms		Conforms		Conforms		Conforms		Conforms		Conforms		Conforms	
Kosher Status		Conforms		Conforms		Conforms		Conforms		Conforms		Conforms		Conforms		Conforms		Conforms	
EP		Conforms		Conforms		Conforms		Conforms		Conforms		Conforms		Conforms		Conforms		Conforms	
USP		Conforms		Conforms		Conforms		Conforms		Conforms		Conforms		Conforms		Conforms		Conforms	
DAB		Conforms		Conforms		Conforms		Conforms		Conforms		Conforms		Conforms		Conforms		Conforms	
cSt.more correctly replaced by mm2/sec		G-II		G-II		G-II		G-II		G-II		G-II		G-II		G-II		G-II	
Batch Number																			
H1 HX-1 3H status		InS 1797664		InS 1797642		1797659		1797660		InS&NSF 1797661		137546 1797662		InS &NSF 1797663					
Sales & Technical Services:																			
ReinhardOil. DK ApS (Ltd.																			
mail@reinhardoil.dk																			
Pro Lube																			
Prolube																			
reinhard oil																			
Prolube																			
Supplied in yellow blue ProLube Iron drums from Stock in DK-7000 Fredericia, Denmark																			
HS Code for ProLube Med. White oils is: 27.10.19.85																			
CAS 8042-47-5																			

Tel:+4570267007