

Lubricant Additives Business

Anderol® 2220 HTCL

Anderol® Industrial lubricants chains

Description

Synthetic High Temperature Chain Lubricant

Anderol® 2220 HTCL is an ISO 220 synthetic ester based chain lubricant specifically designed to provide long-term lubrication even under severe heavy duty and extreme ambient conditions.

Anderol® 2220 HTCL prevents wear, noise, sticking by means of:

- · Film reformation between loadings
- Removal of frictional heat
- · Flushing of wear debris
- · Excellent corrosion and rust protection

The **Anderol**® **HTCL** range is available in the grades ISO VG 100, 150, 220 and 320.

Features and Benefits

- · Protects against external and internal wear.
- Very good drive lubrication.
- Lower oil consumption.
- · Oil film stays well maintained.
- Reduces energy consumption and cost.

Compatibility

The following seals, paints and plastics are recommended for use in contact with **Anderol**® synthetic lubricants. Materials not recommended are also shown. For more information on other materials see our 'Compatibility Guide'.

RECOMMENDED:

Viton, High Nitrile Buna N, Teflon, Epoxy Paint, Oil-Resistant Alkyd, Nylon, Delrin, Celcon, PBT

NOT RECOMMENDED:

Neoprene, SBR Rubber, Low Nitrile Buna N, Acrylic Paint, Lacquer, Polystyrene, PVC, ABS

Page 1 of 3

Edition: 2021-01-18





Lubricant Additives Business

Anderol® 2220 HTCL

Anderol® Industrial lubricants chains

Application

Recommended to be used in difficult environments and conditions including:

- Pulsating, heavy loads and/or high speeds
- · Grit , dust , acids and moisture
- · High temperature

Anderol® 2220 HTCL can be applied by:

- Brush
- Manually
- Oil bath
- · Pressurized system

Nominal Operating Range up to 250 °C.

Technical data*

| PROPERTY | METHOD | ANDEROL 2220 HTCL |
|-----------------------------|-------------|---------------------|
| ISO VG | ASTM D-2422 | 220 |
| Appearance @ 20°C | visual | Clear Yellow Liquid |
| Viscosity @ 40°C, cSt | ASTM D-445 | 227.2 |
| Viscosity @ 100°C, cSt | ASTM D-445 | 26.3 |
| Viscosity Index | ASTM D-2270 | 148 |
| Density @ 15°C, kg/l | ASTM D-1298 | 0.922 |
| Total Acid Number, mg KOH/g | ASTM D-664 | 0.3 |
| Flash Point, °C | ASTM D-92 | 265 |
| Pour Point, °C | ASTM D-97 | -40 |
| | | |

^{*}The analytical data are guide values.

Page 2 of 3

Edition: 2021-01-18





Lubricant Additives Business

Anderol® 2220 HTCL

Anderol® Industrial lubricants chains

Consult safety data sheet (SDS) for additional handling information on **Anderol**[®] **2220 HTCL** For registrations, certificates and approvals please refer to anderol.com

® = registered trade mark

This is a product of Anderol BV Groot Egtenrayseweg 23 5928PA Venlo The Netherlands www.anderol.com

This information and our technical advice – whether verbal, in writing or by way of trials – is subject to change without notice and given in good faith but without warranty or guarantee, express or implied, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to verify the information currently provided - especially that contained in our safety data and technical information sheets - and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with the current version of our General Conditions of Sale and Delivery.

©2021 LANXESS and the LANXESS Logo are trademarks of LANXESS Deutschland GmbH or its affiliates. All trademarks are registered in many countries in the world.

North America +1.833.LANXESS customer.care@lanxess.com Europe, Middle East & Africa +31.77.396.0340 customerservice@anderol.com South & Central America +55.19.3522.5083 atendimento.cliente@lanxess.com Asia Pacific +86.21.6109.6666 Orders.apac@lanxess.com

Page 3 of 3

Edition: 2021-01-18

