

Nytro Libra is an uninhibited transformer oil that conforms to IEC 60296 Edition 4.0. Developed and formulated to deliver solid resistance to oil degradation, Nytro Libra provides good oxidation stability thanks to its natural inhibitors. This increases the possibilities for a longer transformer life with less maintenance.

### Designed for heavy duty

This product has been specially developed for use in oil-filled electrical equipment – including power and distribution transformers, rectifiers, circuit breakers and switchgears.

### Performance and benefits

Good heat transfer. Thanks to low viscosity and viscosity index, this standard grade offers extremely good heat transfer characteristics, ensuring heat is efficiently removed from core and windings.

Reliable oxidation stability. Developed and formulated to deliver good resistance to oil degradation, this grade also provides good oxidation stability for enhanced transformer life and minimum maintenance.

Very good low temperature properties. Naphthenic characteristics allow the transformer to start at the lowest possible temperature – without using pour point depressants.

High dielectric strength. This insulating oil both meets and exceeds the toughest demands on dielectric strength – when stored and handled correctly.

### Product description

Nytro Libra fulfils the requirements for IEC 60296 Edition 4.0 uninhibited oil. Nynas classify this product as a standard grade.

Nytro Libra is rigorously analysed and passes the following corrosion tests:

- ASTM D1275
- IEC 62535
- DIN 51353



In accordance with IEC 60296 Edition 4.0, all additives are declared.

### There's more to us than this

We're delighted you chose one of our transformer oils. If you have any questions about other products and services, get in touch with your local Nynas contact. Besides top quality oils, we offer a wide range of services, including rapid delivery worldwide, sample analysis, training, seminars and much more. All you have to do is ask. Find out more at [www.nynas.com](http://www.nynas.com)

PROPERTY	UNIT	TEST METHOD	SPECIFICATION LIMITS		TYPICAL DATA
			MIN	MAX	
<b>1 - Function</b>					
Viscosity, 40°C	mm <sup>2</sup> /s	ISO 3104		12.0	9.4
Viscosity, -30°C	mm <sup>2</sup> /s	ISO 3104		1800	1050
Pour point	°C	ISO 3016		-40	-51
Water content	mg/kg	IEC 60814		30	<20
Breakdown voltage					
- Before treatment	kV	IEC 60156	30		40-60
- After treatment	kV	IEC 60296	70		>70
Density, 20°C	kg/dm <sup>3</sup>	ISO 12185		0.895	0.876
DDF at 90°C		IEC 60247		0.005	<0.001
<b>2 - Refining/stability</b>					
Appearance		IEC 60296	Clear, free from sediment		complies
Acidity	mg KOH/g	IEC 62021		0.01	<0.01
Interfacial tension	mN/m	EN 14210	40		47
Corrosive sulphur		DIN 51353	non-corrosive		non-corrosive
Potentially corrosive sulphur		IEC 62535	non-corrosive		non-corrosive
Corrosive sulphur		ASTM D 1275	non-corrosive		non-corrosive
DBDS	mg/kg	IEC 62697-1		not detectable	not detectable
Antioxidant	wt %	IEC 60666		not detectable	not detectable
Metal passivator additives	mg/kg	IEC 60666		not detectable	not detectable
2-Furfural and related compounds content	mg/kg	IEC 61198		0.05	<0.05
Aromatic content	%	IEC 60590			9
<b>3 - Performance</b>					
Oxidation stability at 120°C,164 h		IEC 61125 C			
Total acidity	mg KOH/g			1.2	0.65
Sludge	wt %			0.8	0.16
DDF at 90°C				0.500	0.070
<b>4 - Health, safety and environment (HSE)</b>					
Flash point, PM	°C	ISO 2719	135		150
PCA	wt %	IP 346		3	<3
PCB		IEC 61619	not detectable		not detectable



Nytro Libra is an uninhibited insulating oil, meeting IEC 60296 Ed.4 (2012) General specifications. Breakdown voltage after treatment as per definition given in IEC 60296, section 6.4.

Severely Hydrotreated Insulating Oil  
Issuing date: 2017-10-11