



# RTV430

## Description

RTV430 is a two part, high strength, condensation (tin) cure moldmaking product. It can be used with three different catalysts and therefore offers a variety of curing options to be customized for your needs. RTV430 & Beta 5 is a medium durometer (30 Shore A) product offering excellent thermal resistance and dimensional stability. It can be used for casting high-heat resins or for oven-cured process. RTV430 & Beta 11 is a medium durometer (30 Shore A) product, perfect for large, linear parts requiring flexibility and dimensional stability. RTV430 is a two part, high strength, condensation (tin) cure moldmaking product.

## Key Features and Benefits

- Variety of cure options
- Low viscosity, easy flow
- Superior detail reproduction
- High tear strength and flexibility

## Typical Physical Properties

<b>Product Base</b>	<b>RTV430</b>	
Color	white	
Viscosity, cps	55,000	
Specific Gravity	1.08	
<b>Catalyst</b>	<b>Beta5</b>	<b>Beta 11</b>
Color	red	blue
Viscosity, cps	50	20
Specific Gravity	1.22	0.95
Mix Ratio, wt:wt	10:1	10:1
<b>Catalyzed Properties</b>		
Color Mixed	Pink	Light Blue
Viscosity, cps	47,000	47,000
Worklife, minutes	90	70
Potlife, minutes	180	90
Demold time, hours	12	12
Shore A, 36 hours	30	30

Shore A, 24 hours	28	28
Tensile, psi	450	600
Elongation, %	300	360
Tear, pli	130	120
Service Temperature °C (°F)	-60/200 (-75/392)	-60/200 (-75/392)
Linear Shrinkage, % 24 hrs	0.5	0.5
Linear Shrinkage, % 7 days	1.0	1.0

## Potential Applications

- Art reproduction

## Processing Recommendations

- **Mixing:** Select a mixing container 4-5 times larger than the volume of RTV silicone rubber compound to be used. Weigh out the RTV silicone rubber base compound and add the appropriate amount of curing agent. With clean tools, thoroughly mix the RTV base compound and the curing agent, scraping the sides and bottom of the container carefully to produce a homogenous mixture. When using power mixers, avoid excessive speeds which could entrap large amounts of air or cause overheating of the mixture, resulting in shorter pot life.
- **Deaeration:** Air entrapped during mixing should be removed to eliminate voids in the cured product. Expose the mixed material to a vacuum of about 29 in. of mercury. The material will expand, crest, and recede to about the original level as the bubbles break. Degassing is usually complete about two minutes after frothing ceases. Automatic equipment designed to meter, mix, deaerate, and dispense two-component RTV silicone rubber compounds will add convenience to continuous or large volume operations.
- **Curing:** RTV430 with Beta 5 or Beta 11 is designed to cure within 24 hours at room temperature (77°F/25°C) and 50% relative humidity. This system is sensitive to changes in heat and humidity and therefore variations in cure speed may be seen if one or both variables are changed. Enter text or delete paragraph

## Patent Status

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute a permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

## Product Safety, Handling and Storage

Customers should review the latest Material Safety Data Sheet (MSDS) and label for product safety information, safe handling instructions, personal protective equipment if necessary, and any special storage conditions required for safety. MSDS are available at [www.momentive.com](http://www.momentive.com) or, upon request, from any Momentive Performance Materials (MPM) representative. **For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center.** Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

## Limitations

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

**Contact Information**

For product prices, availability, or order placement, contact +45 70 26 70 07.

For literature and technical assistance, visit our website at: [www.ReinhardOil.dk](http://www.ReinhardOil.dk)

**DISCLAIMER**

The information provided herein was believed by Momentive Performance Materials Inc. (collectively with its subsidiaries, "Momentive") to be accurate at the time of preparation or prepared from sources believed to be reliable, but it is the responsibility of the user to investigate and understand other pertinent sources of information, to comply with all laws and procedures applicable to the safe handling and use of the product, and to determine the suitability of the product for user's intended application or use. All products supplied by Momentive are subject to Momentive's standard terms and conditions of sale. **MOMENTIVE MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE OR CONCERNING THE ACCURACY OF ANY INFORMATION PROVIDED BY MOMENTIVE**, except that the product shall conform to Momentive's specifications. Nothing contained herein constitutes an offer for the sale of any product.

**Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.**