

RTV630

**High Strength Silicone Rubber Compound
for Moulding Rubber Parts and Making Prototype Moulds**

Product Description RTV630 blue two component silicone rubber compound cures at room temperature to a high strength silicone rubber. This product is supplied in a matched kit of base (A) component and curing agent (B) component which is designed for use at a convenient 10:1 ratio by weight. RTV630 silicone rubber compound is a medium viscosity product, which will form thin, light-weight moulds with excellent durability. The high tear resistance and inherent release ability of RTV630 rubber compound make it well suited to the manufacture of intricate castings, by reproducing each part exactly to detail. Other typical applications for RTV630 silicone rubber compound include prototype parts, production tools for casting epoxies and rubber rolls. Electrical circuits requiring a tough potting compound with outstanding vibration withstanding capability find RTV630 unequalled.

- Key Performance Properties**
- Convenient 10:1 mixing ratio for use in automatic dispensing equipment or hand operation
 - Good self-leveling characteristics allow precision reproduction of fine model details
 - Long working time at room temperature permits potting or reproduction of larger parts
 - Cure rate can be accelerated with heat
 - May be cured in deep sections
 - May be cured in closed assemblies
 - No cure by-products
 - Low shrinkage

Typical Product Data

UNCURED PROPERTIES

	RTV630A	RTV630B
Colour	Beige	Blue
Consistency	Pourable	Easily Pourable
Viscosity, mPa.s	160,000	6,000
Density, (g/cm ³)	1.29	1.07

UNCURED PROPERTIES WITH CURING AGENT ADDED

	RTV630
Colour	Blue
Consistency	Pourable
Viscosity, mPa.s	150,000
Density, (g/cm ³)	1.28
Work Time @ 25°C , hrs	4



CURED PROPERTIES (Cured 1 hr. @ 100C)	
Mechanical	
Hardness, Shore A, Durometer	60
Tensile Strength, MPa	5.8
Elongation, %	250
Tear Strength, kN/m	20
Shrinkage, %	0.8
Electrical	
Dielectric Strength, kV/mm (1.9 mm thick)	17.7
Dielectric Constant @ 1000 Hz	3.2
Dissipation Factor @ 1000 Hz	0.006
Volume Resistivity, ohm-cm	4.5×10^{15}
Thermal	
Useful Temperature Range, °C	-60 to 204
Thermal Conductivity, W/m.K	0.31
Coefficient of Expansion, cm/cm, °C	21.0×10^{-5}
Specific Heat, cal/g. °C	0.35

Specifications Typical product data values should not be used as specifications. Assistance and specifications are available by contacting Momentive performance materials Technical Service RTV1 and RTV2.

Instructions for Use **Compatibility**

RTV630 silicone rubber compound will cure in contact with most clean dry surfaces. However, certain materials, such as butyl and chlorinated rubber, sulfur-containing materials, amines, and certain metal soap-cured RTV silicone rubber compounds, can cause cure inhibition. Cure inhibition is characterized by a gummy appearance of the RTV silicone at the interface of the silicone rubber compound and the substrate. It is recommended that a sample patch test be performed with RTV630 rubber compound to determine if a barrier coating or other inhibition-preventing measures are necessary before pouring the material.

Mixing

Select a mixing container 4-5 times larger than the volume of RTV silicone rubber compound to be used. Weigh out ten parts of the A component and one part of the B component. Since RTV630 silicone rubber compound is kit-matched, work time (or pot life), cure time, and final properties of the cured RTV silicone rubber compound can be assured only if the A component is used with the B component from the same kit. With clean tools, thoroughly mix the A and B components together, scraping the sides and bottom of the container carefully to produce a homogeneous mixture. When using power mixers, avoid excessive speeds, which could entrap large amounts of air or cause overheating of the mixture, resulting in shorter pot life.

Deaeration

Air entrapped during mixing should be removed to eliminate voids in the cured product. Expose the mixed material to a vacuum of about 25 mm of mercury. The material will expand, crest, and recede to about the original level as the bubbles break. Degassing is usually complete about two minutes after frothing ceases. When using the RTV silicone rubber compound for potting, a deaeration step may be necessary after pouring to avoid capturing air in complex assemblies.

Automatic equipment designed to meter, mix, deaerate, and dispense two-component RTV silicone rubber compounds will add convenience to continuous or large volume operations.

Curing

RTV630 silicone rubber compound will cure sufficiently in 24 hours at 25C to permit handling. To achieve optimum properties an elevated temperature cure or a cure time of two days at room temperature is required. The table below illustrates the effect of temperature on cure time:

Temperature, °C	Cure Time*
25	7 days
65	4 hrs.
100	1 hr.
150	15 min.

* Cure times are only approximate. The actual time is affected by the mass of the unit and the time required to reach the desired temperature.

Bonding

RTV630 silicone rubber compound requires a primer to bond to non-silicone surfaces. Thoroughly clean the substrate with a non-oily solvent such as naphtha or methyl ethyl ketone (MEK), and allow to dry. Then apply a uniform thin film of SS4155 silicone primer, and allow the primer to air dry for one hour or more. Finally, apply freshly catalyzed RTV630 silicone rubber compound to the primed surface and cure as recommended

Handling and Safety

Material Safety Data Sheets are available upon request from Momentive performance materials. Similar information for solvents and other chemicals used with the Momentive performance materials products should be obtained from your supplier. When solvents are used, proper safety precautions must be observed.

Caution:

RTV630B curing agent can generate flammable hydrogen gas upon contact with acidic, basic or oxidizing materials. Such contact should be avoided.

Storage and Warranty Period

The warranted shelf life will be indicated by the 'use before date' on the associated documents with a minimum of 4 months when stored in the original unopened containers below 25° C.

Availability

RTV630 is available in 225 kg, 20 kg, 4.5 kg and 450 g kits.



PRINCIPAL LOCATIONS – Regional Information

North America	World Headquarters 187 Danbury Road Wilton, CT 06897, USA	T 800.295.2392	F 607.754.7517
Latin America	Rodovia Eng. Constâncio Cintra, Km 78,5 Itatiba, SP – 13255-700, Brazil	T +55.11.4534.9650	F +55.11.4534.9660
Europe, Middle East, Africa and India	D-51368 Leverkusen Germany	T 00.800.4321.1000 T +31.164.293.276	F +31.164.241.750
Pacific	Akasaka Park Building - 5-2-20 Akasaka Minato-ku, Tokyo 107-6112 Japan	T +81.3.5544.3100	F +81.3.5544.3101

CUSTOMER SERVICE CENTERS

North America	Charleston, WV 25314, USA E cs-na.silicones@momentive.com		
	• Specialty Fluids	T 800.523.5862	F 304.746.1654
	• UA, Silanes, Resins, and Specialties	T 800.334.4674	F 304.746.1623
	• RTV Products-Elastomers	T 800.332.3390	F 304.746.1623
	• Sealants and Adhesives & Construction	T 877.943.7325	F 304.746.1654
Latin America	E cs-la.silicones@momentive.com		
	• Argentina & Chile	T +54.11.4862.9544	F +54.11.4862.9544
	• Brazil	T +55.11.4534.9650	F +55.11.4534.9660
	• Mexico & Central America	T +52.55.5899.5135	F +52.55.5899.5138
	• Venezuela, Ecuador, Peru, Colombia, & Caribbean	T +58.212.285.2149	F +58.212.285.2149
Europe, Middle East, Africa and India	E cs-eur.silicones@momentive.com	T 00.800.4321.1000 T +31.164.293.276	F +31.164.241750
	E cs-ap.silicones@momentive.com		
Pacific	• Japan	T +81.276.20.6182	
	• China	T +86.21.5050.4666 (ext. 1523)	
	• Korea	T +82.2.6201.4600	
	• Singapore	T +65.6220.7022	
Worldwide Hotline	Worldwide Web www.momentive.com	T 800.295.2392 T +607.786.8131	F +607.786.8309

DISCLAIMER: THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC., MOMENTIVE PERFORMANCE MATERIALS USA INC., MOMENTIVE PERFORMANCE MATERIALS ASIA PACIFIC PTE. LTD., MOMENTIVE PERFORMANCE MATERIALS WORLDWIDE INC., MOMENTIVE PERFORMANCE MATERIALS GmbH & Co. KG, MOMENTIVE PERFORMANCE MATERIALS SUISSE Sarl, THEIR SUBSIDIARIES AND AFFILIATES DOING BUSINESS IN LOCAL JURISDICTIONS (collectively "SUPPLIERS"), ARE SOLD BY THE RESPECTIVE LEGAL ENTITY OF THE SUPPLIER SUBJECT TO SUPPLIERS' STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIERS MAKE NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING SUPPLIERS' PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. AFOREMENTIONED EXCLUSIONS OR LIMITATION OF LIABILITY ARE NOT APPLICABLE TO THE EXTENT THAT THE END-USE CONDITIONS AND/OR INCORPORATION CONDITIONS CORRESPOND TO THE RECOMMENDED CONDITIONS OF USE AND/OR OF INCORPORATION AS DESCRIBED BY SUPPLIER IN ITS PRODUCT DATA SHEET AND/OR PRODUCT SPECIFICATIONS.

EXCEPT AS PROVIDED IN SUPPLIERS' STANDARD CONDITIONS OF SALE, SUPPLIERS AND THEIR REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN.

Each user bears full responsibility for making its own determination as to the suitability of Suppliers' materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Suppliers' products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Suppliers' Standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Suppliers. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Suppliers or any of its subsidiaries or affiliates covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.